

European Approval for Materials  
 Data Sheet  
 EAM-0879-01

This data sheet has been raised in accordance with the requirements of Article 15 of the Pressure Equipment Directive 2014/68/EU. The material described within is not included in a standard which has been harmonised to the afore mentioned directive.

Pure Nickel With Low Carbon For Pressure Equipment  
 EAM Nickel 201 – Hot & Cold rolled plates, sheets & strips

1	Material Designation	1.1	Classification: EAM-0879-01
		1.2	Name: Nickel 201
		1.3	Material Ref. No.: 2.4068
		1.4	UNS Ref. No.: N02201
		1.5	ISO/TR 15608:2000 Group 41
2	Standards to which consideration and or reference has been given.	<p>This EAM incorporates by dated or undated reference provisions from other publications. These references are cited in the text and in the following list. For dated references, subsequent amendments to, or revisions of any of these publications apply to this EAM only when incorporated in an amendment or revision to this EAM. For undated references the latest edition of the publication applies (including amendments).</p> <p>2.1 LC-Ni 99 VdTÜV 345 – 06/1999 (Origin)</p> <p>2.2 EN 10002-1:2001</p> <p>2.3 EN 10002-5:1992</p> <p>2.4 EN 10045-1:1990</p> <p>2.5 EN 10204:1991</p> <p>2.6 EN 10003-1:1995</p> <p>2.7 EN ISO 6507-1:1998</p>	

This document may be freely reproduced.  
 An original copy of this EAM may be obtained from TÜV UK Ltd at [www.tuv-nord.com/uk](http://www.tuv-nord.com/uk) follow the links for Inspection and PED.  
 This document has unrestricted use by public administration and other Notified Bodies within the context of PED 2014/68/EU.

3	Limiting Dimensions	Form	Dimensions										
			Thickness (mm)			Diameter (mm)							
		Strip / Sheet / Plate	Up to and including 50mm			-							
4	Melting Method	4.1 Electric Arc Process											
		4.2 Induction Furnace Process											
5	Production Method / Delivery Condition	5.1 Hot Rolled		} Soft annealed (see section 10)									
		5.2 Cold Rolled											
		The products shall be free from surface and internal defects which might impair their usability											
6	Application Temp.	6.1 -10° to 600°C											
		6.2 The material is also suitable for use below -10°C. For such cases, impact values and verification procedures shall be agreed at the time of ordering.											
7	Chemical Composition	% Composition by Weight											
			Ni	C	Si	Mn	S	P	Fe	Cu	Mg	Ti	
		Ladle	Minimum	99.0									
			Maximum		0.020	0.20	0.35	0.010	0.015	0.40	0.25	0.15	0.10
		Product	Minimum	98.4									
		Maximum		0.025	0.23	0.38	0.013	0.018	0.47	0.28	0.18	0.13	
8	Mechanical and Technological Requirements	8.1 Tensile Properties at Room Temperature											
		Rp0.2 N/mm <sup>2</sup>		Rp1.0 N/mm <sup>2</sup>			Rm N/mm <sup>2</sup>		A %				
		Min 80		Min 105			340/540		Min 40 (both 5d and 5.65√So)				
		8.2 Transverse (see section 9).											
	Verification Test Direction	8.3 Minimum proof and tensile strength values at Elevated Temperature °C <sup>1)</sup>											
		100		200		300		400		500		600	
	Tensile Properties	Requirement N/mm <sup>2</sup>											
		Rp0.2	70		65		60		55		(50) (40)		
		Rp1.0	95		90		85		(80)		(75) (65)		
		Rm <sup>2)</sup>	290		275		260		240		210 150		
		1) For design calculations no interpolation between stated values is permitted (unless the design code explicitly provides for it). The values at the higher temperature shall be used. 2) Rm values for reference only. The values in brackets are above the intersection with the calculated creep properties for 100,000 hours (see section 15). The property values are taken from VdTÜV 345-06.99											

N.B. 1 N/mm<sup>2</sup> = 1 MPa

8	Other Properties	8.4 Minimum Impact Properties at room temperature (Charpy V) EN 10045-1							
		Longitudinal direction: = KV 120 J Transverse direction : = KV 80 J							
		8.5 Hardness Brinell HB – EN 10003-1 Or Hardness Vickers HV – EN ISO 6507-1							
		Both HB and HV: 130 max							
		8.6 Modulus of Elasticity KN/mm <sup>2</sup>							
		Temperature °C	20	100	200	300	400	500	600
		E-Modulus	196	192	188	180	172	162	150
		Reproduced from VdTÜV 345 06/99 (with mistake in source document regarding order of units corrected).							
9	Testing	9.1 Type of Inspection and Test							
		Test / Inspection	Frequency			Reference			
		Cast Analysis	One per cast			Section 7			
		Product Analysis	One per cast (if required and agreed at the time of ordering by the purchaser).			Section 7			
		Positive Material I/D	All items			Section 7			
		9.2 Tensile Test at Room Temperature							
		Product Form	Frequency			Reference			
		Sheet / Plate <10mm	1 Transverse test per cast per size per 20 sheets / plates or part there of.			Section 8.1 and EN 10002-1			
		Sheet / Plate > 10mm	1 Transverse test per plate.						
		Coil Strip	1 Transverse test at each end of the coil.						
		9.3 Elevated Temperature Tensile Tests							
		Product Form	Frequency			Reference			
		All product forms with operating temperatures ≥ 100°C	1 test per cast from the product with the largest thickness			Section 8.3 and EN 10002-5			

9	Testing	9.4 Impact Testing			
		Verification of impact properties is only required when specified by the purchaser at the time of ordering. The values stated in section 8.4 shall be the minimum average of 3 specimens, with only one individual specimen value allowed up to a maximum of 30% lower.			Reference
		Section 8.4 and EN 10045-1			
		9.5 Hardness Test			
		Product Form	Frequency	Reference	
		All	All Mechanical Test Samples / Coupons	Section 8.5	
		9.6 Visual Inspection <sup>1)</sup>			
		Product Form	Frequency	Reference	
		All	All Items		
		9.7 Dimensional Inspection <sup>1)</sup>			
		Product Form	Frequency	Reference	
		All	All Items		
		1) 100% inspection of all products by the manufacturer. Dimensional tolerances for all product forms shall be agreed between the manufacturer and purchaser at the time of ordering.			
10	Heat Treatment	Method	Temperatures	Holding Times	Cooling
		Soft Annealing	700 to 850°C	2 to 4 min/mm of thickness	Air
		Stress Relief Annealing	550 to 650°C	30 min to 3 hrs.	
11	Joining	11.1 Welding			
		<p>This material has, historically, proven suitable for fusion welding by: the MMA (111) welding process with coated electrodes using the appropriate filler material, e.g. material No.:2.4156. Also the processes TIG (141) and MIG (131) using the appropriate filler material, e.g. No.:2.4155</p> <p>Information supplied by the consumable manufacturer on the filler wires suitability must be considered, especially with regard to sulphur sensitivity and both low and elevated temperature properties.</p> <p>The material does not normally require pre heat and should be welded in the soft annealed condition.</p> <p>Stress relief annealing may take place after welding.</p> <p>Where cold forming exceeds 5%, stress relief annealing shall be performed prior to welding.</p> <p>Consultation with the material manufacturer's technical department is recommended when choosing a filler wire or welding process.</p>			

12	Forming	12.1 Hot and Cold
		<p>The material is suitable for both hot and cold forming subject to the following provisions:</p> <ol style="list-style-type: none"> <li>1) Hot forming shall occur between 800 to 1250°C followed by soft annealing (see section 10).</li> <li>2) Where cold forming deformation exceeds 5% a stress relief anneal or soft anneal shall be performed (see section 10).</li> <li>3) The material is sensitive to sulphur above 400°C, therefore the surface should be carefully cleaned before any welding or heat treatment.</li> <li>4) It is important that the furnace atmospheres for processing are sulphur free.</li> </ol>
13	Marking	<p>Material shall be marked with the following information:</p> <p>The material is suitable for both hot and cold forming subject to the following provisions:</p> <ol style="list-style-type: none"> <li>1) Manufacturer's Identification Mark</li> <li>2) Cast / Melt Number</li> <li>3) Test or Manufacturing Batch Number</li> <li>4) Material Grade</li> <li>5) EAM Reference No.</li> </ol> <p>Markings shall normally be by permanent ink marking or Vibro-etching.</p>
		<p>14.1 Document Type</p> <ol style="list-style-type: none"> <li>1) Material manufacturers shall supply documentation affirming compliance with this EMA.          This document shall normally be in the form of an inspection certificate in accordance with EN 10204 3.1.B.</li> </ol> <p>Note: Where a material manufacturer has an appropriate quality assurance system, certified by a competent body, established with the community and having undergone a specific assessment for materials, certificates issued by the manufacturer are presumed to certify conformity with the requirements of section 4.3 of Annex 1 of the PED.</p> <ol style="list-style-type: none"> <li>2) If an inspection document in accordance with EN 10204 3.1.C or 3.2 is specified, the purchaser shall notify the manufacturer of the name and address of the organisation or person who is to carry out the inspection and produce the inspection document. In the case of the inspection report 3.2 it shall be agreed which party shall issue the certificate.</li> </ol> <p>Note: The affirmation of the compliance of the delivery with this EMA is not a mandatory requirement of EN 10204. Such affirmation – as is required by the PED 2014/68/EU in Annex 1 4.3 first paragraph – can be added into the text of the material certificate, when it is signed by the manufacturer. It could also be provided in a separate document. In the case the material certificate is signed by a third party, the affirmation shall be contained in a document which is (also) signed by the manufacturer.</p>
14	Inspection Documents	

14	Inspection Documents	14.2 Contents of Inspection Documents
		<ol style="list-style-type: none"> <li>1) Details of the manufacturer</li> <li>2) Details of the purchaser (if required)</li> <li>3) Description and dimensions of the product</li> <li>4) Supply conditions</li> <li>5) Ladle analysis</li> <li>6) Product analysis (if required)</li> <li>7) Results from mechanical property tests</li> <li>8) Heat treatment applied</li> <li>9) Results from other applicable tests (e.g. PMI)</li> <li>10) Marking and identification</li> <li>11) Affirmation of compliance with this EAM</li> <li>12) Declaration of the status of the Manufacturer's Quality System (including the name of the competent body having certified the quality system, if applicable).</li> </ol>

15	Calculated Creep Properties	Temperature °C	Calculated 1% creep strain strength characteristics (multiplied by factor 1.5) <sup>1)</sup> N/mm <sup>2</sup>	
			10 <sup>4</sup> h	10 <sup>5</sup> h
		350	-	85
		360	-	80
		370	-	75
		380	85	70
		390	80	65
		400	75	60
		410	71	56
		420	67	52
		430	63	48
		440	59	44
		450	55	40
		460	51	36
		470	47	32
		480	43	29
		490	39	26
		500	35	23
		510	31	20
		520	28	17
		530	25	15
		540	22	13
		550	19	11
		560	17	9
		570	15	8
		580	13	7
		590	11	6.5
		600	10	6

1) The figures above are calculated creep strain strength characteristics values which correspond to the lower scatter band of the 1% creep strain limit multiplied by 1.5.

N.B. Between the 1% creep strain limit and the creep rupture strength there is a difference which is greater than 1.5 x 1% creep strain limit. In order to avoid unacceptable deformations the creep rupture strength cannot be used for calculation.

For design calculations no interpolation between stated values is permitted (unless the design code explicitly provides for it). The values at the higher temperature shall be used.

The characteristics in the table above are reproduced from VdTÜV 345 06/99